



## DATA SHEET

### **EPDM**

**(Ethylene Propylene Diene Terpolymer)**

**4215-EC**

Color:

Black

Specifications:

ASTM D-1056-00

2A2

25% Compression Deflection (PSI)

5 - 9

Shore 00 Durometer (Approximate)

40 - 60

Density (Approximate p.c.f.)

9 - 14

Water Absorption By Weight

5%

Temperature Range

-90 to 275 F

Weather Resistance:

UV  
Ozone

Excellent  
Excellent

Tensile Strength (Typical)

65 PSI

Elongation (Typical)

180%

Flammability:

FM VSS No. 302

Pass

Temperature range listed is continuous. Moderately higher or lower temperatures are attainable on an intermittent basis.

*American National Rubber disclaims responsibility for results of use of this information, which is furnished without charge, or of any product mentioned herein. It is the user's responsibility to make and be guided by his own testing before making a final decision on the type of material to be used in any application.*

10/2014